

HP Office 75gsm – Technical Characteristics

General Specification:

HP Office is an uncoated woodfree paper developed for the usage in the multi-task office environment.

Grammage	g/m ²	75.0	ISO 536/2000
Thickness	Microns	98	ISO 534/88
Whiteness	D65 10°	161	ISO 11475/99
Moisture	%	4.0	ISO287/85
Brightness	ISO	98	ISO 2469/94
Opacity	%	90	ISO2471/98
Porosity (Gurley)	Sec/100cc	12	TAPPI T460-02
Roughness T	ml/min	190	ISO 8791/2/90
Roughness B ml/min	ml/min	190	ISO 8791/2/90
HST Sizing (Felt)	sec	140	TAPPI T530 om-96
Tearing Strength MD	mN	540	ISO 1974/90
Tearing Strength CD	mN	600	ISO 1974/90
Tensile Strength MD	kN/m	5.5	ISO 1924/2/94
Tensile Strength CD	kN/m	2.7	ISO 1924/2/94
Stiffness MD	gf.cm	2.5	ISO 2493/92
Stiffness CD	gf.cm	1.1	ISO 2493/92
Formation Index	MK	28	-